

Serge 10%		Technical info	
Composition		Glassfibre 42% - PVC 58%	
Openness factor	NBN EN 410	10.00%	
Weight	NF EN 12127	490.00 g/m ²	
Thickness	ISO 5084	0.83 mm	
Density	ISO 2286-3	WARP 18.00 yarn/cm	WEFT 12.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Color fastness to artificial weathering	ISO 105 B04	>7	
Roll length		50 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007		
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 method 2		
└ Original		WARP 9.60 daN	WEFT 7.60 daN
└ After climatic chamber -30°C		WARP 8.60 daN	WEFT 7.10 daN
└ After climatic chamber +70°C		WARP 8.80 daN	WEFT 7.00 daN
Elongation up to break	ISO 1421		
└ Original		WARP 5.20 %	WEFT 4.90 %
└ After colour fastness to artificial weathering		WARP 5.80 %	WEFT 5.00 %
└ After color fastness to artificial light		WARP 6.70 %	WEFT 5.20 %
└ After climatic chamber -30°C		WARP 5.00 %	WEFT 4.80 %
└ After climatic chamber +70°C		WARP 4.80 %	WEFT 4.20 %
Breaking strength	ISO 1421		
└ Original		WARP 312.00 daN/5cm	WEFT 200.00 daN/5cm
└ After colour fastness to artificial weathering		WARP 289.00 daN/5cm	WEFT 190.00 daN/5cm
└ After color fastness to artificial light		WARP 289.00 daN/5cm	WEFT 185.00 daN/5cm
└ After climatic chamber -30°C		WARP 271.00 daN/5cm	WEFT 174.00 daN/5cm
└ After climatic chamber +70°C		WARP 217.00 daN/5cm	WEFT 139.00 daN/5cm